

AD-A105 870

ARMY MATERIALS AND MECHANICS RESEARCH CENTER WATERTOWN MA F/G 11/9  
ACCELERATION OF THE EPOXY RESIN-DICYANDIAMIDE CURE CYCLE BY TRI--ETC(U)  
JUN 81 B R LALIBERTE, R E SACHER, J BORNSTEIN  
AMMRC-TR-81-30

NL

UNCLASSIFIED

1 OF 1  
AD-A105 870

END  
DATE  
FILMED  
11 84  
DTIC

**(12) LEVEL #**

AMMRC TR 81-30

AD

AD A105870

**ACCELERATION OF THE EPOXY  
RESIN-DICYANDIAMIDE CURE CYCLE  
BY TRISUBSTITUTED UREAS**

BERNARD R. LaLIBERTE, ROBERT E. SACHER, and  
JOSEPH BORNSTEIN

POLYMER RESEARCH DIVISION

June 1981

DTIC  
ELECTE  
OCT 20 1981  
S B D

Approved for public release; distribution unlimited.

ARMY MATERIALS AND MECHANICS RESEARCH CENTER  
Watertown, Massachusetts 02172

DTIC FILE COPY

X  
81 10 20

The findings in this report are not to be construed as an official Department of the Army position, unless so designated by other authorized documents.

Mention of any trade names or manufacturers in this report shall not be construed as advertising nor as an official indorsement or approval of such products or companies by the United States Government.

#### DISPOSITION INSTRUCTIONS

Destroy this report when it is no longer needed.  
Do not return it to the originator.

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

14 REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER AMMRC-TR-81-30	2. GOVT ACCESSION NO. AD-A105870	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) ACCELERATION OF THE EPOXY RESIN-DICYANDIAMIDE CURE CYCLE BY TRISUBSTITUTED UREAS.	5. TYPE OF REPORT & PERIOD COVERED Final Report	
7. AUTHOR(s) Bernard R. LaLiberte, Robert E. Sacher, and Joseph Bornstein	8. CONTRACT OR GRANT NUMBER(s) 16	
9. PERFORMING ORGANIZATION NAME AND ADDRESS Army Materials and Mechanics Research Center Watertown, Massachusetts 02172 DRXMR-RP	10. PROGRAM ELEMENT PROJECT TASK AREA & WORK UNIT NUMBERS D/A Project: 1L162105AH84 AMCMS Code: 62105A Agency Accession: DA OD4815	
11. CONTROLLING OFFICE NAME AND ADDRESS U. S. Army Materiel Development and Readiness Command, Alexandria, Virginia 22333	12. REPORT DATE Jun 81	
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office) 12 15	13. NUMBER OF PAGES 9	
15. SECURITY CLASS. (of this report) Unclassified		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report)  Approved for public release; distribution unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Epoxy resins Hardeners Accelerating agents Reaction kinetics		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number)  (SEE REVERSE SIDE)		

DD FORM 1 JAN 73 1473

EDITION OF 1 NOV 65 IS OBSOLETE

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

403105

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)

Block No. 20

ABSTRACT

The addition of accelerators such as Monuron, N-(4-chlorophenyl)-N',N'-dimethylurea, or Diuron, N-(3,4-dichlorophenyl)-N',N'-dimethylurea, to epoxy resin-dicyandiamide mixtures significantly decreases the hardening temperature of these systems. These trisubstituted urea accelerators are believed to serve mainly as a latent source of dimethylamine. This amine is believed to play a very important role in the cure cycle. One pathway to dimethylamine is a low-temperature cyclocondensation reaction between the trisubstituted urea and the epoxy functionality to form a 2-oxazolidone; this reaction partially hardens the resin. The significance of this source of dimethylamine in the overall mechanism of epoxy hardening was illustrated by differential scanning calorimetry. Several epoxy formulations were examined at various heating rates. Arrhenius plots of the data indicated that the slope of a two-component mixture consisting of resin and Monuron was approximately the same as that of a three-component system composed of resin, dicyandiamide, and Monuron. In contrast, the slope of a two-component resin-dicyandiamide system was found to be considerably larger. Thus the reaction of Monuron with the resin is an important factor that must be considered in any explanation of the acceleration of the hardening process of dicyandiamide-containing resins.

Accession For	
NTIS GRA&I	<input checked="checked" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution/	
Availability Codes	
Avail and/or	
Dist	Special
A	


UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)

## INTRODUCTION

Interest in the mechanism of the hardening of epoxy resin-dicyandiamide (Dicy)/accelerator systems originated from a previous study\* which had been conducted because the literature did not disclose the reason Diuron, N-(3,4-dichlorophenyl)-N',N'-dimethylurea, had the ability to lower the hardening temperature of tetraglycidyl methylene dianiline (TGMDA)-Dicy systems. The cure behavior of TGMDA-Dicy/Diuron mixtures composed of resin having various molecular weights was examined by differential scanning calorimetry (DSC) at a heating rate of 2°C/min. The cure temperatures of these systems were found to lie in a narrow range of 129° to 133°C. The TGMDA-Diuron reaction releases dimethylamine and subsequently it was found that a large variation in the composition of the resin system only slightly altered the hardening temperature. In fact, a TGMDA-Diuron reaction conducted in the thermal analyzer (DSC) at 2°C/min showed an exotherm at 129°C which is the same as that obtained in the presence of Dicy. This reaction mixture solidified on reaching room temperature. In contrast, the reaction of Dicy with pure TGMDA resin showed an exotherm at 170°C. These observations led us to believe that dimethylamine played a significant role in the cure cycle. Accordingly, attention was directed to the pathways leading to dimethylamine and these will be discussed.

Thickening occurs concomitantly with the evolution of dimethylamine in the TGMDA-Diuron reaction and in this process the accelerator was assumed to react with the epoxy groups of the resin. The isolation of a clean reaction product in such a complex polymeric mixture was not practical. Therefore, the reaction of Diuron with a simpler epoxy-containing compound, p-tert-butylphenyl glycidyl ether (PTBGE), was investigated by mass spectrometry (MS) in the hope of finding a reaction product that might be associated with the liberation of dimethylamine.† The MS examination did indeed indicate the presence of a 2-oxazolidone derivative whose formation suggested that dimethylamine must be a coproduct.




Similarly, the MS examination of the reaction mixture of Monuron, N-(4-chlorophenyl)-N',N'-dimethylamine, and PTBGE revealed a molecular ion ascribable to a 2-oxazolidone derivative. Evidence that the MS interpretations were correct was subsequently obtained by actually preparing substantial quantities of 2-oxazolidones and the accompanying dimethylamine by the reaction of phenyl glycidyl ether (PGE) with the above aryl ureas.‡

\*LaLIBERTE, B. R., and BERGQUIST, P. R. *A Cure Study of Tetraglycidyl Methylene Dianiline System with Diuron and Dicyandiamide*. Army Materials and Mechanics Research Center, AMMRC TN 78-5, June 1978.

†LaLIBERTE, B. R. *The Reaction of Diuron with Epoxy Groups*. Army Materials and Mechanics Research Center, AMMRC TN 79-1, January 1979.

‡LaLIBERTE, B. R., and BORNSTEIN, J., manuscript in preparation.


Another potential pathway to dimethylamine is the dissociation of the trisubstituted ureas to form an aryl isocyanate as shown with Diuron:



Due to the difference in the melting points of the urea accelerators we had suspected that Diuron (mp 154°C) might dissociate more readily than Monuron (mp 172°C). Examination of the decomposition of the aryl ureas by DSC and by thermogravimetric analysis (TGA) was hindered by the fact that sublimation competes with dissociation. However, we did infer from the TGA analyses that both Diuron and Monuron liberate the amine at about the same temperature. Thus, the TGA analyses did not seem to support our speculative view that dissociation was related to the melting point.

For this reason, each of the accelerators (0.1 g) was heated slowly in test tubes in an oil bath; evolution of the amine was monitored with moistened litmus paper. Both Diuron and Monuron were found to release minute quantities of dimethylamine at about 174°C. It is interesting that Nonuron, N-phenyl-N',N'-dimethylurea, (mp 134°C) begins to release amine at approximately 150°C. These experiments suggest that the dissociation temperature of the urea depends on the substitution pattern of the aromatic ring rather than on the melting point of the urea.


As a third possible source of dimethylamine we had considered a condensation reaction between the aryl urea and Dicy which would be expected to afford a linear guanidine derivative as shown:



DSC examination of an intimate mixture of Diuron and Dicy (1:4 mole ratio, respectively) failed to reveal a distinct exotherm and the same was true for a mixture of Monuron and Dicy. It should be pointed out that the failure to observe an exotherm is not necessarily an indication that a chemical reaction has not occurred. Subsequently, a literature search for the expected guanidine was conducted and this brought to light the investigation of Son and Weber.<sup>1</sup> They reported that Dicy and Monuron,

1. SON, P., and WEBER, C. D. *Some Aspects of Monuron-Accelerated Dicyandiamide Cure of Epoxy Resins*. J. Applied Polymer Science, v. 17, 1973, p. 1305-1313.

upon heating in diglyme, afforded 1-cyano-3-(p-chlorocarbanilino)-guanidine in 35.5% yield along with dimethylamine in 5.6% yield. Their support for the guanidine structure was based on mass spectrometry, which gave the expected value of 237 for the molecular weight, and on infrared analysis, which showed a carbonyl band at  $1690\text{ cm}^{-1}$ . Interestingly, they failed to report a peak in the infrared spectrum for the nitrile group which clearly is one of the salient features of their proposed structure. In addition, no elemental analysis was given for this substance which was described as not melting at  $300^\circ\text{C}$ . Prompted by these omissions, we repeated the reaction of Monuron with Dicy in diglyme. We found that at  $120^\circ\text{C}$  only small amounts of dimethylamine were evolved; analysis of the reaction mixture over a period of several hours revealed only unchanged Monuron and Dicy at this temperature. However, when the temperature of the reaction mixture was raised to  $163^\circ\text{C}$ , reflux ensued and copious volumes of the amine were evolved; after one hour the reaction was complete and a substantial amount of a light tan solid was isolated which, after purification (washing with methanol followed by recrystallization from boiling water), appeared from mass and infrared spectroscopy to be identical with the product isolated previously by Son and Weber.<sup>1</sup> Elemental analysis supported the guanidine structure reported by Son and Weber; however, infrared analysis indicated the nitrile function to be absent. For this reason we wish to assign tentatively the following isomeric cyclic structure to the product from the Monuron-Dicy reaction.



In this connection, it is noteworthy that fusion at  $170^\circ\text{C}$  of equimolar amounts of Monuron and Dicy affords the same cyclic compound and dimethylamine in quantitative yield.

## RESULTS AND DISCUSSION

A mixture of Monuron and a colorless liquid epoxy resin (EPON 828) heated at  $130^\circ\text{C}$  quickly turned amber and became viscous. Small bubbles of amine gas could be observed. Upon cooling, the resulting viscous solution turned to a hard, solid mass. The infrared analysis of this reaction mixture yielded the characteristic carbonyl band<sup>2</sup> associated with 2-oxazolidones at  $1745\text{ cm}^{-1}$ . In comparison, the neat resin heated to  $130^\circ\text{C}$  remained colorless and did not solidify upon cooling to room temperature. Another experiment was conducted in which the resin was treated with a small amount of a 2-oxazolidone and then heated to  $130^\circ\text{C}$ ; this mixture also failed to solidify upon cooling. Noteworthy is the fact that the introduction of dimethylamine into the neat resin was found to harden the epoxy resin at room temperature. These experiments illustrate that the formation of the 2-oxazolidone ring in the resin medium has little significance to the hardening process outside of the fact that the cyclocondensation reaction is an important source of dimethylamine.

2. SANDLER, S. R. *Preparation of Mono and Poly-2-Oxazolidones from 1,2-Epoxydes and Isocyanates*. J. Polymer Science, A-1, v. 5, 1967, p. 1481-1485.



As previously mentioned, the Monuron-Dicy reaction liberates only trace amounts of dimethylamine at 120°C and, in contrast, DSC examination of a two-component EPON 828-Monuron mixture at the extremely slow heating rate of 0.5°C/min indicated the cyclocondensation reaction occurs in the proximity of 92°C. The introduction of Dicy to form a three-component EPON 828-Dicy/accelerator system displayed an exotherm at about the same temperature (94°C) as that of the two-component mixture. The heating of the three-component system was terminated at 130°C at which temperature the sample was found to be a solid mass. It should be pointed out that EPON 828 cannot be hardened by Dicy at 130°C within two hours. In this study, in order to investigate the activation of Dicy by dimethylamine, it was necessary to evaluate the resin-Dicy/accelerator and the resin-accelerator systems as two separate and distinct entities.

All mixtures were prepared with the diglycidyl ether of bisphenol-A (EPON 828) whose molecular weight was determined to be 350.6 on the basis of epoxy number. The first formulation was a three-component system consisting of 15 moles of resin, 4.0 moles of Dicy, and 1.0 mole of Monuron. The related two-component system was prepared with 15 moles of resin and 1.0 mole of Monuron. Also included in this study was a concentrated three-component system consisting of only 2.5 moles of the resin, 4.0 moles of Dicy, and 1.0 mole of Monuron. The curing agent combination of the concentrated system is 67%, whereas in the dilute three-component mixture it is 20% (on a molar basis).

The examination by DSC of these formulations was conducted at various heating rates and the resulting data treated according to the following expression:<sup>3</sup>

$$\log_{10} \text{Rate} = A/T + B$$

where:

Rate = heating rate (°C/min)

A = constant, related to activation energy

T = temperature (°K)

B = constant, related to the Arrhenius frequency factor.

The validity of the experiments depends on a linear relationship of the plot of the  $\log_{10}$  rate versus the  $1 \times 10^3/^\circ\text{K}$  values. A computer program was used to analyze the data for reliability and from this data the graphs were obtained.

The equation for the activation energy ( $E_a$ ) is:<sup>4</sup>

$$\text{Slope} = -E_a/2.303R$$

where R = the gas constant, 1.987 cal degree<sup>-1</sup> mole<sup>-1</sup>.

The slopes for the Monuron system, calculated from the thermal measurements of the three mixtures, were found to be:

Dilute (20%):	3510
Concentrated (67%):	4340
Monuron + Resin only:	3610

3. CARPENTER, J. F. *Quality Control of Structural Nonmetallics*. Contract N00019-76-C-0138, manuscript prepared for the Naval Air System Command, Washington, D.C., June 1977, p. 15.

4. MARON, S. H., and PRUTTON, C. F. *Principles of Physical Chemistry*. Fourth Edition, MacMillan Company, New York, 1965, p. 572.

AD  
 Army Materials and Mechanics Research Center  
 Watertown, Massachusetts 02172  
 ACCELERATION OF THE EPOXY RESIN-DICYANDIAMIDE  
 CURE CYCLE BY TRISUBSTITUTED UREAS -  
 Bernard R. Laliberte, Robert E. Sacher, and  
 Joseph Bornstein  
 Technical Report AMMRC TR 81-30, June 1981, 9 pp -  
 illus-table, D/A Project 1L162105AH84,  
 ANCMS Code 62105A

UNCLASSIFIED  
 UNLIMITED DISTRIBUTION  
 Key words  
 Epoxy resins  
 Hardeners  
 Accelerating agents

The addition of accelerators such as Monuron, N-(4-chlorophenyl)-N',N'-dimethylurea, or Diuron, N-(3,4-dichlorophenyl)-N',N'-dimethylurea, to epoxy resin-dicyandiamide mixtures significantly decreases the hardening temperature of these systems. These trisubstituted urea accelerators are believed to serve mainly as a latent source of dimethylamine. This amine is believed to play a very important role in the cure cycle. One pathway to dimethylamine is a low-temperature cyclocondensation reaction between the trisubstituted urea and the epoxy functionality to form a 2-oxazolidone; this reaction partially hardens the resin. The significance of this source of dimethylamine in the overall mechanism of epoxy hardening was illustrated by differential scanning calorimetry. Several epoxy formulations were examined at various heating rates. Arrhenius plots of the data indicated that the slope of a two-component mixture consisting of resin and Monuron was approximately the same as that of a three-component system composed of resin, dicyandiamide, and Monuron. In contrast, the slope of a two-component resin-dicyandiamide system was found to be considerably larger. Thus the reaction of Monuron with the resin is an important factor that must be considered in any explanation of the acceleration of the hardening process of dicyandiamide-containing resins.

AD  
 Army Materials and Mechanics Research Center  
 Watertown, Massachusetts 02172  
 ACCELERATION OF THE EPOXY RESIN-DICYANDIAMIDE  
 CURE CYCLE BY TRISUBSTITUTED UREAS -  
 Bernard R. Laliberte, Robert E. Sacher, and  
 Joseph Bornstein  
 Technical Report AMMRC TR 81-30, June 1981, 9 pp -  
 illus-table, D/A Project 1L162105AH84,  
 ANCMS Code 62105A

UNCLASSIFIED  
 UNLIMITED DISTRIBUTION  
 Key words  
 Epoxy resins  
 Hardeners  
 Accelerating agents

The addition of accelerators such as Monuron, N-(4-chlorophenyl)-N',N'-dimethylurea, or Diuron, N-(3,4-dichlorophenyl)-N',N'-dimethylurea, to epoxy resin-dicyandiamide mixtures significantly decreases the hardening temperature of these systems. These trisubstituted urea accelerators are believed to serve mainly as a latent source of dimethylamine. This amine is believed to play a very important role in the cure cycle. One pathway to dimethylamine is a low-temperature cyclocondensation reaction between the trisubstituted urea and the epoxy functionality to form a 2-oxazolidone; this reaction partially hardens the resin. The significance of this source of dimethylamine in the overall mechanism of epoxy hardening was illustrated by differential scanning calorimetry. Several epoxy formulations were examined at various heating rates. Arrhenius plots of the data indicated that the slope of a two-component mixture consisting of resin and Monuron was approximately the same as that of a three-component system composed of resin, dicyandiamide, and Monuron. In contrast, the slope of a two-component resin-dicyandiamide system was found to be considerably larger. Thus the reaction of Monuron with the resin is an important factor that must be considered in any explanation of the acceleration of the hardening process of dicyandiamide-containing resins.

AD  
 Army Materials and Mechanics Research Center  
 Watertown, Massachusetts 02172  
 ACCELERATION OF THE EPOXY RESIN-DICYANDIAMIDE  
 CURE CYCLE BY TRISUBSTITUTED UREAS -  
 Bernard R. Laliberte, Robert E. Sacher, and  
 Joseph Bornstein  
 Technical Report AMMRC TR 81-30, June 1981, 9 pp -  
 illus-table, D/A Project 1L162105AH84,  
 ANCMS Code 62105A

UNCLASSIFIED  
 UNLIMITED DISTRIBUTION  
 Key words  
 Epoxy resins  
 Hardeners  
 Accelerating agents

The addition of accelerators such as Monuron, N-(4-chlorophenyl)-N',N'-dimethylurea, or Diuron, N-(3,4-dichlorophenyl)-N',N'-dimethylurea, to epoxy resin-dicyandiamide mixtures significantly decreases the hardening temperature of these systems. These trisubstituted urea accelerators are believed to serve mainly as a latent source of dimethylamine. This amine is believed to play a very important role in the cure cycle. One pathway to dimethylamine is a low-temperature cyclocondensation reaction between the trisubstituted urea and the epoxy functionality to form a 2-oxazolidone; this reaction partially hardens the resin. The significance of this source of dimethylamine in the overall mechanism of epoxy hardening was illustrated by differential scanning calorimetry. Several epoxy formulations were examined at various heating rates. Arrhenius plots of the data indicated that the slope of a two-component mixture consisting of resin and Monuron was approximately the same as that of a three-component system composed of resin, dicyandiamide, and Monuron. In contrast, the slope of a two-component resin-dicyandiamide system was found to be considerably larger. Thus the reaction of Monuron with the resin is an important factor that must be considered in any explanation of the acceleration of the hardening process of dicyandiamide-containing resins.

AD  
 Army Materials and Mechanics Research Center  
 Watertown, Massachusetts 02172  
 ACCELERATION OF THE EPOXY RESIN-DICYANDIAMIDE  
 CURE CYCLE BY TRISUBSTITUTED UREAS -  
 Bernard R. Laliberte, Robert E. Sacher, and  
 Joseph Bornstein  
 Technical Report AMMRC TR 81-30, June 1981, 9 pp -  
 illus-table, D/A Project 1L162105AH84,  
 ANCMS Code 62105A

UNCLASSIFIED  
 UNLIMITED DISTRIBUTION  
 Key words  
 Epoxy resins  
 Hardeners  
 Accelerating agents

The addition of accelerators such as Monuron, N-(4-chlorophenyl)-N',N'-dimethylurea, or Diuron, N-(3,4-dichlorophenyl)-N',N'-dimethylurea, to epoxy resin-dicyandiamide mixtures significantly decreases the hardening temperature of these systems. These trisubstituted urea accelerators are believed to serve mainly as a latent source of dimethylamine. This amine is believed to play a very important role in the cure cycle. One pathway to dimethylamine is a low-temperature cyclocondensation reaction between the trisubstituted urea and the epoxy functionality to form a 2-oxazolidone; this reaction partially hardens the resin. The significance of this source of dimethylamine in the overall mechanism of epoxy hardening was illustrated by differential scanning calorimetry. Several epoxy formulations were examined at various heating rates. Arrhenius plots of the data indicated that the slope of a two-component mixture consisting of resin and Monuron was approximately the same as that of a three-component system composed of resin, dicyandiamide, and Monuron. In contrast, the slope of a two-component resin-dicyandiamide system was found to be considerably larger. Thus the reaction of Monuron with the resin is an important factor that must be considered in any explanation of the acceleration of the hardening process of dicyandiamide-containing resins.

It is especially noteworthy that the slope of the Monuron-resin mixture is nearly the same as that of the dilute three-component system.

This study was undertaken because of the belief that these two resin systems would have similar slopes and this has now been verified. It will be shown below that the resin-Dicy reaction has the largest slope. Consequently, these results are consistent with our earlier observations that the resin-accelerator reaction is responsible for the activation of Dicy. Since the concentrated three-component system has a slope larger than that of the corresponding dilute mixture, it would be expected that chemical reactions become more difficult to initiate as the availability of epoxy groups is decreased.

The slopes of three systems containing Monuron are shown together. The formulation of the mixtures and reaction temperature at various heating rates are denoted by an experimental number; both are indicated in Table 1 and in Figure 1.

Table 1. THERMAL ANALYSIS RESULTS

System	Experiment	Moles of			Rate (deg C/min)	Temp. (deg C)
		Resin	Dicy	Accelerator		
a. Monuron	1	15	4	1	0.5	94
					2	121
					5	139
					10	145
					20	171
	2	2.5	4	1	1	108
					2	116
					5	133
					10	145
					20	155
	3	15	0	1	1	109
					2	131
					5	143
					10	157
					20	172
b. Diuron	4	15	4	1	1	108
					2	119
					5	137
					10	145
					20	165
	5	2.5	4	1	1	105
					2	117
					5	131
					10	144
					20	159
c. Nonuron	6	15	4	1	1	114
					2	128
					5	143
					10	157
					20	172
	7	2.5	4	1	1	106
					2	115
					5	128
					10	141
					20	156
d. Dicyandiamide	8	15	4	0	0.5	161
					1	176
					2	180
					5	190
						163




Figure 1. Thermal analysis results.

The slopes of the dilute and concentrated three-component systems of Diuron and Nonuron were found to be:

	<u>Dilute (20%)</u>	<u>Concentrated (67%)</u>
Diuron Systems	3910	4000
Nonuron Systems	3920	4240

All data points of Nonuron fall on a straight line, therefore the slope of these lines clearly illustrates the effect of concentration. In the case of Diuron, the data represents a magnification of the difficulties encountered in the preparation of homogeneous mixtures. Prior to this study, we had become aware of the effects of high level concentration on reaction temperatures. Although concentration is of secondary importance, this factor was considered in this study because Son and Weber's<sup>1</sup> speculation concerning the source of dimethylamine was based on two components, the urea and Dicy, and failed to take into account systems in which epoxy resin was also present. Their

interpretation of the DSC results is ambiguous as to the role of the resin-Monuron reaction. In connection to the synergistic effect between Monuron and Dicy the results of this particular study, "Mechanism of Monuron-Accelerated Dicyandiamide Cure of Epoxy Resins," will be published.

The final experiment conducted in this study was the examination of the two-component system prepared with 15 moles of resin and 4.0 moles of Dicy. Based on duplicate runs involving four different heating rates, the slope was found to lie between 7270 and 7890. Clearly, this system has the largest slope. Consequently, the magnitude of this slope illustrates that Dicy had indeed undergone activation in all three component systems used in this study.

In conclusion, the liberation of dimethylamine by the reaction of the trisubstituted ureas with the resin is an important factor that has to be taken into consideration in providing any explanation of the lowering of the cure temperature of dicyandiamide-containing resins.

#### EXPERIMENTAL

Differential scanning calorimetric experiments were conducted in open aluminum pans with a DuPont 990 thermal analyzer fitted with a 902 DSC plug-in module in a static atmosphere. The exothermic reaction temperatures were taken at the apex of the heating curves.

#### ACKNOWLEDGMENT

We thank Dr. B. H. Halpin, Jr., for his encouragement during the preparation of this manuscript. Dr. G. L. Hagnauer analyzed the thermal data and Miss D. Dempsey performed the TGA examination. Mr. A. Deome kindly performed the MS analysis.

# DISTRIBUTION LIST

No. of Copies	To
1	Office of the Under Secretary of Defense for Research and Engineering, The Pentagon, Washington, D. C. 20301
12	Commander, Defense Technical Information Center, Cameron Station, Building 5, 5010 Duke Street, Alexandria, Virginia 22314
1	Metals and Ceramics Information Center, Battelle Columbus Laboratories, 505 King Avenue, Columbus, Ohio 43201
	Deputy Chief of Staff, Research, Development, and Acquisition, Headquarters, Department of the Army, Washington, D. C. 20310
1	ATTN: DAMA-ARZ
	Commander, Army Research Office, P. O. Box 12211, Research Triangle Park, North Carolina 27709
1	ATTN: Information Processing Office
	Commander, U. S. Army Materiel Development and Readiness Command, 5001 Eisenhower Avenue, Alexandria, Virginia 22333
1	ATTN: DRCLDC
	Commander, U. S. Army Materiel Systems Analysis Activity, Aberdeen Proving Ground, Maryland 21005
1	ATTN: DRXS-MP, H. Cohen
	Commander, U. S. Army Electronics Research and Development Command, Fort Monmouth, New Jersey New Jersey 07703
1	ATTN: DELSD-L
1	DELS-D-E
	Commander, U. S. Army Missile Command, Redstone Arsenal, Alabama 35809
4	ATTN: DRSMI-TB, Redstone Scientific Information Center
1	Technical Library
1	DRSMI-RLD, Mr. D. Loveless
1	DRSMI-EAM, Mr. H. Dedman
	Commander, U. S. Army Armament Research and Development Command, Dover, New Jersey 07801
2	ATTN: Technical Library
1	DRDAR-SCM, J. D. Corrie
1	DRDAR-LCA, Mr. Harry E. Peibly, Jr., PLASTEC, Director
1	Mr. A. M. Anzalone, PLASTEC
	Commander, U. S. Army Natick Research and Development Command, Natick, Massachusetts 01760
1	ATTN: Technical Library
	Director, U. S. Army Ballistic Research Laboratory, Aberdeen Proving Ground, Maryland 21005
1	ATTN: DRDAR-TSB-S (STINFO)
	Commander, U. S. Army Foreign Science and Technology Center, 220 7th Street, N. E., Charlottesville, Virginia 22901
1	ATTN: Military Tech, Mr. Marley
	Director, Eustis Directorate, U. S. Army Air Mobility Research and Development Laboratory, Fort Eustis, Virginia 23604
1	ATTN: Mr. J. Robinson, DAVDL-E-MOS (AVRADCOM)
	Naval Research Laboratory, Washington, D. C. 20375
1	ATTN: Dr. J. M. Krafft - Code 5830
	Chief of Naval Research, Arlington, Virginia 22217
1	ATTN: Code 471

No. of  
Copies

To

Commander, U. S. Air Force Wright Aeronautical Laboratories, Wright-Patterson Air Force Base,  
Ohio 45433  
2 ATTN: AFWAL/MLSE, E. Morrissey  
1 AFWAL/MLC  
1 AFWAL/MLLP, D. M. Forney, Jr.  
1 AFWAL/MLBC, Stanley Schulman

National Aeronautics and Space Administration, Washington, D. C. 20546  
1 ATTN: Mr. B. G. Achhammer  
1 Mr. G. C. Deutsch - Code RW

National Aeronautics and Space Administration, Marshall Space Flight Center,  
Huntsville, Alabama 35812  
1 ATTN: R. J. Schwinghammer, EH01, Dir, M&P Lab  
1 Mr. W. A. Wilson, EH41, Bldg. 4612

1 Ship Research Committee, Maritime Transportation Research Board, National Research Council,  
2101 Constitution Ave., N. W., Washington, D. C. 20418

1 Librarian, Materials Sciences Corporation, Blue Bell Campus, Merion Towle House, Blue Bell,  
Pennsylvania 19422

1 Dr. Clayton May, Lockheed Missiles and Space Company, Inc., Dept. 47-01, Bldg. 150, P. O. Box 504,  
Sunnyvale, California 94088

1 R. W. Hoffman, Hercules, Inc., P. O. Box 98, Magna, Utah 84044

1 Judy S. Chen, M.S. 73-43, Boeing Commercial Airplane Company, Seattle, Washington 98008

1 Robert Holden, Grumman Aerospace Corporation, Bethpage, New York 11714

1 Dr. David Kaelbe, Rockwell Science Center, 1049 Camino Dos Rios, P. O. Box 1085,  
Thousand Oaks, California 91360

1 David Crabtree, Northrop Corporation, Hawthorne, California 90250

1 Don Crozier, Lockheed California Company, B/229, PH2 (Dept. No. 74-71), P. O. Box 551,  
Burbank California 91520

1 J. F. Carpenter, McDonnell Douglas Corporation, McDonnell Aircraft Company, P. O. Box 516,  
St. Louis, Missouri 63166

1 Dr. T. Helminiak, AFWAL/MLBC, Wright-Patterson Air Force Base, Ohio 45433

1 Dr. R. Van Deusen, AFWAL/MLBP, Wright-Patterson Air Force Base, Ohio 45433

1 Dr. Chet Poranski, Naval Research Laboratory, Code 6110, Washington, D. C. 20375

1 Dr. Anthony Davis, Procurement Executive, Ministry of Defense, Non-Metallic Materials Branch,  
Waltham Abbey, Essex, England

1 Dr. William Moniz, Chemistry Division, Code 6120, Naval Research Laboratory,  
Washington, D. C. 20375

1 J. M. Mills, Jr., Information Control Office, Union Carbide Corporation, Nuclear Division,  
Y-12 Plant, Oak Ridge, Tennessee 37830

1 Paul Scherer, McDonnell Douglas Corporation, Huntington Beach, California 92646

1 Dr. J. Cernosek, Bell Helicopter Textron, Dept. 80, P. O. Box 482, Fort Worth, Texas 76101

1 K. Clark, Naval Air Development Center, Warminster, Pennsylvania 18974

1 Charles Bersch, Naval Air Systems Command, Washington, D. C. 20361

Director, Army Materials and Mechanics Research Center, Watertown, Massachusetts 02172  
2 ATTN: DRXMR-PL  
3 Authors

END

DATE  
FILMED

11-81

DTIC